


ULTRA PREMIUM  
SATIN

RESOURCE CODE 11736-Line  
APRIL 2024  
PAGE 1 OF 4



Description & Uses

Wattyl Aqua Trim Satin is a 100% acrylic interior and exterior trim and wall paint that provides the speed and ease of water-based technology in a tough, durable enamel coating. This smooth satin finish is non-yellowing and dries hard so painted surfaces will not stick together.

Ideal for use on interior and exterior trim and woodwork: doors, architraves, skirting boards, windows and furniture. Interior Walls: kitchens, bathrooms and laundries. Suitable for use in most areas where oil-based enamels were traditionally used. Not suitable for areas which will be subjected to hot objects e.g benchtops.

Features & Benefits

- |  |  |
|--|--|
| <ul style="list-style-type: none"> <li>• Superior application</li> <li>• Smooth durable finish</li> <li>• Fast Drying</li> </ul> | <ul style="list-style-type: none"> <li>• Non-yellowing</li> <li>• Low odour</li> </ul> |
|--|--|

Colours

White, Light, Mid and Strong bases. Tint using Ecotint® to Wattyl Colour Designer® range of colours or other competitor colours.

Satin (Gloss level 25 - 35 at 60 degrees).

Environmental Data & Certifications



Approved to Australia Paint Approval Scheme Specification APAS 0260/2. Australian Standard AS3730.2



Verified to the Good Environmental Choice Australia Program (GECA) Specification GECA 23-2005.



VOC – less than 45g/litre untinted or when tinted with Ecotint. VOC (Volatile Organic Compounds) calculations are based on APAS definition and are in accordance with Green Building Council requirements. Green Building Council standard for the maximum VOC level in trim paints is 75g/litre.

ULTRA PREMIUM  
SATIN

RESOURCE CODE 11736-Line

APRIL 2024

PAGE 2 OF 4



White, Light, Mid and Strong Tint Bases Verified to Eco Choice Aotearoa (ECA) Specification EC-07-18.  
Licence No:0709054

## Properties &amp; Performance Guide

Dry & Recoat Times	<p>Surface Dry - 30 minutes            Recoat - 2 hour            Fully Cured - 7 days</p> <p>Figures are quoted at 25°C and at 50% humidity. Drying will take longer at lower temperatures or higher relative humidity.</p>
Coverage per Coat	Up to 16 M <sup>2</sup> /L depending on the surface texture, porosity and method of application.
Film Thickness	<p>Wet Film Thickness (WFT) - 63 microns minimum            Dry Film Thickness (DFT) - 23 microns minimum</p>
Thinning	If required, thin with up to 5% water.
Clean Up	<p>Clean up with cold water away from drains.  <b>Protect Our Environment:</b> Do not pour leftover paint down the drain. To dispose of unwanted paint see <a href="http://paintback.com.au">paintback.com.au</a>.            Empty paint containers should be left open in a well ventilated area to dry out. When dry, recycle containers via recycling programs. Check with your local council first.</p>
VOC (Volatile Organic Compounds)	VOC < 45g/Litre. The VOC level has been calculated theoretically from raw material information in accordance with APAS D181.

## Recommended Substrate Conditions &amp; Preparation

Surfaces are to be suitably prepared in accordance with proper trade practices. Ensure the surface is clean, dry and free from dust, dirt and grease. Remove loose, peeling or flaking material. Sand the surface smooth and remove all dust. Sand enamel painted surfaces to remove gloss. For best results, finish sanding with 240 or finer abrasive paper. Fill holes and cracks with a suitable filler and sand lightly to an even and smooth finish. If mould is present, clean surface with a suitable mould treatment as per manufacturer's instructions. Test soundness of previously painted surfaces by cutting a small X in the paint with a sharp blade. Stick a piece of tape firmly over the X and pull off. If the paint pulls away, the surface is unsound. Repeat at random in a number of areas. Unsound surfaces should be stripped for best results.

## Application Guide

Stir well before and during use with a broad paddle reaching to the bottom of the can and lifting until contents are completely mixed.

ULTRA PREMIUM  
SATIN

RESOURCE CODE 11736-Line

APRIL 2024

PAGE 3 OF 4

Apply two full, even coats with brush, roller or spray.  
Use a short nap (6-9mm) synthetic roller or quality synthetic brush. Moisten brushes or rollers lightly before use, and to keep them working freely, rinse occasionally in clean water. Spread the paint quickly to an even film over a small section, laying off lightly into freshly painted sections.  
Avoid applying excessively thick coats as running or sagging may occur. Splashes should be removed immediately with a damp cloth. To achieve a smoother finish, lightly sand after undercoating and between finishing coats with 240 or finer abrasive paper and remove dust.  
Do not apply when temperature is below 10°C or above 35°C or when humidity is very high.  
In exterior application avoid painting when dew or rain is likely.

Surface Type	Preparatory Coats
Previously painted, sound water-based surfaces and pre-primed MDF.	No sealer or undercoat is required on sound surfaces. Apply one coat of Wattyl Primer Sealer Undercoat where required to create an even base over patched or damaged surfaces or to maximise opacity of topcoat.
Previously painted, sound oil-based surfaces.	Apply one coat of Wattyl Primer Sealer Undercoat.
Bare interior timber and MDF.	Apply one coat of Wattyl Primer Sealer Undercoat.
Bare exterior and tannin rich timbers.	Apply one coat of Wattyl Acrylic Timber Primer. Some tannin rich timbers may require a second primer coat.
Bare paper-faced plasterboard.	Apply one coat of Wattyl Primer Sealer Undercoat.
Bare plaster.	Apply one coat of Wattyl Master Prep Pigmented Sealer or Wattyl Acrylic Plaster Sealer.
Ferrous metals.	Apply two coats of Killrust® Heavy Duty Primer or Wattyl Master Prep Metal Primer.
Non-ferrous metals.	Apply one coat of Wattyl Killrust Etch Primer® or Wattyl Galvanised Iron Primer.

## Additional Data

Available in 1 & 4 litres. White also available in 2 & 10 litre containers.  
Tinted paint is non-refundable, so choose your colours carefully.  
If using more than one can for the final coat, check that the colour is correct in all cans and mix the paint together to ensure colour consistency before starting.  
Avoid exposure to steam and condensation for 48 hours after application of final coat.  
Leave 7 days after application of final coat before washing. Wash using a sponge or soft cloth with warm water and mild detergent. Avoid harsh scrubbing and strong household cleaners.  
Containers must be secured and stored upright during transit.  
Containers must not be exposed to excessive heat or cold.  
Store in a secure, cool and well ventilated place. Keep container tightly closed.  
The use of proprietary additives other than those manufactured by Wattyl is not recommended.  
Do not use for any other purpose other than as specified in our literature.

## Safety Data

<b>First Aid Instructions</b>	For advice, contact the Poisons Information Centre on 131 126 (Australia), 0800 764 766 (New Zealand), or a doctor. If swallowed, do not induce vomiting. Give a glass of water to drink. If in eyes, wash out immediately with water. If inhaled remove from contaminated area to fresh air. If skin contact occurs, remove contaminated clothing and flush contaminated skin with water.
-------------------------------	--

ULTRA PREMIUM  
SATIN

RESOURCE CODE 11736-Line

APRIL 2024

PAGE 4 OF 4

<b>Safety Directions</b>	Keep out of reach of children. Avoid contact with skin and eyes. Ensure adequate ventilation during use. Avoid prolonged breathing of vapour. Wash hands thoroughly after use.
<b>Further Information</b>	For the latest information refer to the Safety Data Sheet available on our websites. Australia: <a href="http://www.wattyl.com.au">www.wattyl.com.au</a> or contact Wattyl Assist on 132 101. New Zealand: <a href="http://www.wattyl.co.nz">www.wattyl.co.nz</a> or contact Wattyl Assist on 0800 825 7727.

1. This information is provided with respect to the listed Hempel (Wattyl) Australia and Hempel (Wattyl) New Zealand products. Hempel (Wattyl) Australia and Hempel (Wattyl) New Zealand, hereon referred to as "Hempel (Wattyl)," recommends that:

(a) You review the Technical Data Sheets (TDS) and Safety Data Sheets (SDS) before you use or handle the product; (b) the product be used only in accordance with the information provided by Hempel (Wattyl); (c) the product be transported and handled in accordance with the SDS and relevant TDS; and (d) you thoroughly test the product, using the recommended application method on a sample of intended substrate, before using the product.

2. The information in the TDS was prepared using information gathered during product development. While Hempel (Wattyl) endeavour to update this information and maintain the accuracy of its contents, Hempel (Wattyl) cannot guarantee that the information is wholly comprehensive.

3. Hempel (Wattyl) recommend that you conduct such additional investigations as may be necessary to satisfy yourself of the accuracy, currency and comprehensiveness of the information on which you rely in using and handling the product. If you require further information please contact your nearest office of Hempel (Wattyl).

4. To the full extent permitted by law, the liability of Hempel (Wattyl) for breach of a condition or warranty implied into the contract for sale between Hempel (Wattyl) and you by law is limited at the election of Hempel (Wattyl) to: (a) the replacement of the product; or (b) payment of the cost of replacing the product.

All brands and product names are registered trademarks of Hempel (Wattyl) Australia Pty Ltd ABN 40 000 035 914 and Hempel (Wattyl) New Zealand Pty Ltd 942 904 073 3692.

WATTYL ASSIST: Ph: 132 101 (AUSTRALIA)  
Ph: 0800 825 7727 (NEW ZEALAND)