

ULTRA PREMIUM
KITCHEN & BATHROOM SATIN

RESOURCE CODE 117865

APRIL 2024

PAGE 1 OF 4



Description & Uses

Wattyl I.D Advanced Kitchen & Bathroom Satin is a high performance, durable interior paint that is ideal for rooms exposed to high humidity and frequent cleaning. Delivering a desirable satin finish, this low VOC paint is resistant to moisture, mould and mildew.

Suitable for use in domestic or commercial environments and where hygienic cleaning practices are used. Whatever your needs, Wattyl I.D Advanced is the confident choice.

Features & Benefits

- Bacteria, mould & mildew resistant
- Easy to clean

- Durable
- Low VOC

Colours

White. Tint using Ecotint® to Wattyl Colour Designer® range of colours or other competitor colours.

Satin (Gloss level 30 - 40 at 60 degrees).

Environmental Data & Certifications



Green Building
Council Australia

VOC – less than 1g/litre untinted or when tinted with Ecotint. VOC (Volatile Organic Compounds) calculations are based on APAS definition and are in accordance with Green Building Council requirements. Green Building Council standard for the maximum VOC level in interior satin wall paint is 16g/litre.



Eco®
Choice
Aotearoa

White Tint Base Verified to Eco Choice Aotearoa (ECA) Specification EC-07-18.
Licence No:0709054

ULTRA PREMIUM KITCHEN & BATHROOM SATIN

RESOURCE CODE 117865

APRIL 2024

PAGE 2 OF 4

Properties & Performance Guide

Dry & Recoat Times	Surface Dry - 30 minutes Recoat - 2 hours Fully Cured - 7 days Figures are quoted at 25°C and at 50% humidity. Drying will take longer at lower temperatures or higher relative humidity.
Coverage per Coat	Up to 16 M ² /L depending on the surface texture, porosity and method of application.
Film Thickness	Wet Film Thickness (WFT) - 63 microns minimum Dry Film Thickness (DFT) - 26 microns minimum
Thinning	If required, thin with up to 5% water.
Clean Up	Clean up with cold water away from drains. Protect Our Environment: Do not pour leftover paint down the drain. To dispose of unwanted paint see paintback.com.au . Empty paint containers should be left open in a well ventilated area to dry out. When dry, recycle containers via recycling programs. Check with your local council first.
VOC (Volatile Organic Compounds)	VOC < 1g/Litre. The VOC level has been calculated theoretically from raw material information in accordance with APAS D181.

Recommended Substrate Conditions & Preparation

Surfaces are to be suitably prepared in accordance with proper trade practices.

Ensure the surface is clean, dry and free from dust, dirt and grease. Remove loose, peeling or flaking material. Sand the surface smooth and remove all dust. Sand enamel painted surfaces to remove gloss. Fill holes and cracks with a suitable filler and sand lightly to an even finish.

All new cement surfaces need to be fully cured (typically 4–6 weeks) prior to painting. Ensure surfaces are free of bond breakers, formwork release agents and curing compounds.

If mould is present, clean surface with a suitable mould treatment as per manufacturer's instructions.

Test soundness of previously painted surfaces by cutting a small X in the paint with a sharp blade. Stick a piece of tape firmly over the X and pull off. If the paint pulls away, the surface is unsound. Repeat at random in a number of areas. Unsound surfaces should be stripped for best results.

Application Guide

Stir well before and during use with a broad paddle reaching to the bottom of the can and lifting until contents are completely mixed.

Apply two full, even coats by brush, roller or spray.

Use a quality synthetic brush or synthetic roller.

For best results when rolling, use a 12mm pile synthetic roller on smooth and semi-smooth surfaces.

Longer nap synthetic rollers may be used on rough surfaces.

Ensure that brushes and rollers are dry or only slightly damp with water before use.

Use a 13 or 15 thou Tip for airless spray.

Do not apply when temperature is below 10°C or above 35°C or when humidity is very high.

ULTRA PREMIUM KITCHEN & BATHROOM SATIN

RESOURCE CODE 117865

APRIL 2024

PAGE 3 OF 4

Surface Type	Preparatory Coats
Previously painted surfaces water-based.	No undercoat required on correctly prepared sound surfaces. Apply one coat of Wattyl Water-Based Prep Acrylic Sealer Undercoat Low VOC where required to create an even base over patched or damaged surfaces or to maximise opacity of topcoat.
Previously painted surfaces oil-based.	Apply one coat of Wattyl Water-Based Prep Acrylic Sealer Undercoat Low VOC.
Bare timber and MDF.	Apply one coat of Wattyl Water-Based Prep Acrylic Sealer Undercoat Low VOC. On tannin rich timber first apply one coat of Wattyl Water-Based Prep Acrylic Timber Primer.
Bare cement render, brick, fibre cement and masonry.	Apply one coat of Wattyl Water-Based Prep Acrylic Sealer Undercoat Low VOC.
Bare paper-faced plasterboard.	Apply one coat of Wattyl Water-Based Prep Acrylic Sealer Undercoat Low VOC.
Bare plaster.	Apply one coat of Wattyl Master Prep Pigmented Sealer or Wattyl Water-Based Prep Acrylic Plaster Sealer.
Ferrous metals.	Apply two coats of Killrust Heavy Duty Primer or Wattyl Master Prep Metal Primer.
Non-ferrous metals.	Apply one coat of Wattyl Killrust Etch Primer or Wattyl Water-Based Prep Galvanised Iron Primer.

Additional Data

Available in 4 & 10 litres.

Tinted paint is non-refundable, so choose your colours carefully.

If using more than one can for the final coat, check that the colour is correct in all cans and mix the paint together to ensure colour consistency before starting.

Avoid exposure to steam and condensation for 48 hours after application of final coat.

Leave 7 days after application of final coat before washing. Wash using a sponge or soft cloth with warm water and mild detergent. Avoid harsh scrubbing and strong household cleaners.

Containers must be secured and stored upright during transit.

Containers must not be exposed to excessive heat or cold.

Store in a secure, cool and well ventilated place. Keep container tightly closed.

The use of proprietary additives other than those manufactured by Wattyl is not recommended.

Do not use for any other purpose other than as specified in our literature.

ULTRA PREMIUM
KITCHEN & BATHROOM SATIN

RESOURCE CODE 117865

APRIL 2024

PAGE 4 OF 4

Safety Data

First Aid Instructions	For advice, contact the Poisons Information Centre on 131 126 (Australia), 0800 764 766 (New Zealand), or a doctor. If in eyes, wash out immediately with water. Remove contact lenses if present and easy to do so, continue rinsing. If skin contact occurs remove contaminated clothing and flush contaminated skin with water. If inhaled remove from contaminated area to fresh air. If swallowed, do not induce vomiting. Give a glass of water to drink.
Safety Directions	Keep out of reach of children. Wash hands thoroughly after use. Avoid contact with skin and eyes. Ensure adequate ventilation during use. Avoid prolonged breathing of vapour.
Further Information	For the latest information refer to the Safety Data Sheet available on our websites. Australia: www.wattyl.com.au or contact Wattyl Assist on 132 101. New Zealand: www.wattyl.co.nz or contact Wattyl Assist on 0800 825 7727.

1. This information is provided with respect to the listed Hempel (Wattyl) Australia and Hempel (Wattyl) New Zealand products. Hempel (Wattyl) Australia and Hempel (Wattyl) New Zealand, hereon referred to as "Hempel (Wattyl)," recommends that:

(a) You review the Technical Data Sheets (TDS) and Safety Data Sheets (SDS) before you use or handle the product; (b) the product be used only in accordance with the information provided by Hempel (Wattyl); (c) the product be transported and handled in accordance with the SDS and relevant TDS; and (d) you thoroughly test the product, using the recommended application method on a sample of intended substrate, before using the product.

2. The information in the TDS was prepared using information gathered during product development. While Hempel (Wattyl) endeavour to update this information and maintain the accuracy of its contents, Hempel (Wattyl) cannot guarantee that the information is wholly comprehensive.

3. Hempel (Wattyl) recommend that you conduct such additional investigations as may be necessary to satisfy yourself of the accuracy, currency and comprehensiveness of the information on which you rely in using and handling the product. If you require further information please contact your nearest office of Hempel (Wattyl).

4. To the full extent permitted by law, the liability of Hempel (Wattyl) for breach of a condition or warranty implied into the contract for sale between Hempel (Wattyl) and you by law is limited at the election of Hempel (Wattyl) to: (a) the replacement of the product; or (b) payment of the cost of replacing the product.

All brands and product names are registered trademarks of Hempel (Wattyl) Australia Pty Ltd ABN 40 000 035 914 and Hempel (Wattyl) New Zealand Pty Ltd 942 904 073 3692.

WATTYL ASSIST: Ph: 132 101 (AUSTRALIA)
Ph: 0800 825 7727 (NEW ZEALAND)