

CEILING WHITE

RESOURCE CODE 47121239

SEPTEMBER 2021

PAGE 1 OF 3



Description & Uses

Wattyl Trade Ceiling White is an interior flat acrylic ceiling paint designed for the trade painter. Wattyl Trade Ceiling White is without side sheen and is designed for use on ceilings where glancing or critical lighting can highlight surface imperfections.

Features & Benefits

- | | |
|---|--|
| <ul style="list-style-type: none">• Water-based• Easy to apply | <ul style="list-style-type: none">• Good coverage• Hides minor surface irregularities |
|---|--|

Colours

White – Not suitable for tinting. Where a tinted colour is required for ceilings, use Wattyl Trade Tintable White.

Flat (Gloss level <3 at 60 degrees).

CEILING WHITE

RESOURCE CODE 47121239

SEPTEMBER 2021

PAGE 2 OF 3

Properties & Performance Guide

Dry & Recoat Times	Surface Dry - 30 minutes Recoat - 2 hours Fully Cured - 7 days Figures are quoted at 25°C and at 50% humidity. Drying will take longer at lower temperatures or higher relative humidity.
Coverage per Coat	Up to 14 M ² /L depending on the surface texture, porosity and method of application.
Film Thickness	Wet Film Thickness (WFT) - 65 microns minimum Dry Film Thickness (DFT) - 20 microns minimum
Thinning	Thinning is generally not required. If necessary to aid spray atomisation, thin with up to 5% water.
Clean Up	Clean up with cold water away from drains. Protect Our Environment: Do not pour leftover paint down the drain. To dispose of unwanted paint see paintback.com.au . Empty paint containers should be left open in a well ventilated area to dry out. When dry, recycle containers via recycling programs. Check with your local council first.
VOC (Volatile Organic Compounds)	VOC < 30g/Litre.

Recommended Substrate Conditions & Preparation

Surfaces are to be suitably prepared in accordance with proper trade practices.

Ensure the surface is clean, dry and free from dust, dirt and grease. All loose, peeling or flaking material must be removed. Sand enamel painted or surfaces to remove gloss. Fill holes and cracks with a suitable filler and sand lightly to an even finish.

All new cement surfaces need to be fully cured (typically 4–6 weeks) prior to painting. Ensure surfaces are free of bond breakers, formwork release agents and curing compounds.

If mould is present, clean surface with household bleach then rinse well with clean water.

Test soundness of previously painted surfaces by cutting a small X in the paint with a sharp blade. Stick a piece of tape firmly over the X and pull off. If the paint pulls away, the surface is unsound. Repeat at random in a number of areas. Unsound surfaces should be stripped for best results.

Application Guide

Stir well before and during use with a broad paddle reaching to the bottom of the can and using an upward lifting action.

Apply two full, even coats to the surface preferably by airless spray as brush or roller marks can mar the overall smoothness of the finish.

Use a 17 or 19 thou Tip for airless spray.

Do not apply when temperature is below 10°C or above 35°C or when humidity is very high.

Surface Type	Preparatory Coats
Previously painted surfaces, new paper-faced plasterboard, unpainted brick, cement render, fibre cement or masonry.	Apply one coat of Wattyl Trade Acrylic Sealer Undercoat.
Interior bare timber and MDF.	Apply one coat of Wattyl Trade Acrylic Sealer Undercoat. On tannin rich timber first apply one coat of Wattyl Ultra Primer Sealer Undercoat.
Bare plaster.	Apply one coat of Wattyl Master Prep Pigmented Sealer.

CEILING WHITE

RESOURCE CODE 47121239

SEPTEMBER 2021

PAGE 3 OF 3

Additional Data

Available in 15 litre container.

If the paint has been tinted, check that the colour is suitable for your requirements before application. For best results and colour consistency, tinted paint should be boxed and thoroughly mixed on site.

When spraying large confined areas e.g. house lots, it is recommended to break the masking after each coat to allow air circulation and allow positive drying.

For ceilings in wet areas or where a washable ceiling finish is required, use Wattyl Trade Interior Low Sheen Acrylic or Wattyl Trade Interior Satin Acrylic.

Avoid exposure to steam and condensation for 48 hours after application of final coat.

Containers must be secured and stored upright during transit.

Containers must not be exposed to excessive heat or cold.

Store in a secure, cool and well ventilated place. Keep container tightly closed.

The use of proprietary additives other than those manufactured by Wattyl is not recommended.

Do not use for any other purpose other than as specified in our literature.

Safety Data

First Aid Instructions

For advice, contact the Poisons Information Centre on 131 126 (Australia), 0800 764 766 (New Zealand), or a doctor.

If swallowed, do not induce vomiting. Give a glass of water to drink.

If in eyes, wash out immediately with water.

If inhaled remove from contaminated area to fresh air.

If skin contact occurs, remove contaminated clothing and flush contaminated skin with water.

Safety Directions

Keep out of reach of children.

Avoid contact with skin and eyes.

Ensure adequate ventilation during use.

Avoid prolonged breathing of vapour.

Wash hands thoroughly after use.

Further Information

For the latest information refer to the Safety Data Sheet available on our websites.

Australia: www.wattyl.com.au or contact Wattyl Assist on 132 101.

New Zealand: www.wattyl.co.nz or contact Wattyl Assist on 0800 825 7727.

1. This information is provided with respect to the listed Hempel (Wattyl) Australia and Hempel (Wattyl) New Zealand products. Hempel (Wattyl) Australia and Hempel (Wattyl) New Zealand, hereon referred to as "Hempel (Wattyl)," recommends that:

(a) You review the Technical Data Sheets (TDS) and Safety Data Sheets (SDS) before you use or handle the product; (b) the product be used only in accordance with the information provided by Hempel (Wattyl); (c) the product be transported and handled in accordance with the SDS and relevant TDS; and (d) you thoroughly test the product, using the recommended application method on a sample of intended substrate, before using the product.

2. The information in the TDS was prepared using information gathered during product development. While Hempel (Wattyl) endeavour to update this information and maintain the accuracy of its contents, Hempel (Wattyl) cannot guarantee that the information is wholly comprehensive.

3. Hempel (Wattyl) recommend that you conduct such additional investigations as may be necessary to satisfy yourself of the accuracy, currency and comprehensiveness of the information on which you rely in using and handling the product. If you require further information please contact your nearest office of Hempel (Wattyl).

4. To the full extent permitted by law, the liability of Hempel (Wattyl) for breach of a condition or warranty implied into the contract for sale between Hempel (Wattyl) and you by law is limited at the election of Hempel (Wattyl) to: (a) the replacement of the product; or (b) payment of the cost of replacing the product.

All brands and product names are registered trademarks of Hempel (Wattyl) Australia Pty Ltd ABN 40 000 035 914 and Hempel (Wattyl) New Zealand Pty Ltd 942 904 073 3692.

WATTYL ASSIST: Ph: 132 101 (AUSTRALIA)

Ph: 0800 825 7727 (NEW ZEALAND)