

Taubmans Tradex 100% Acrylic Semi Gloss

Page 1 of 3

DESCRIPTION

- 100% acrylic semi gloss for exterior use with excellent exterior durability.

PRINCIPAL CHARACTERISTICS

- Ideal for previously painted or new primed exterior surfaces
- Ideal for timber weatherboards
- Suitable for concrete render, fibre cement
- Excellent durability and gloss retention.
- Suitable for use on surfaces that collect drinking water.
- Easily applied.

COLOURS AND GLOSS

- Colour – White, may be tinted to a range of pastel colours
- Finish – Semi Gloss (gloss at 60° 30-35%)

BASIC DATA

- **Surface dry** Thirty (30) minutes at 20°C and 65% relative humidity.
- **Recoat** Two (2) hours at 20°C and 65% relative humidity. Allow up to twice as long for cooler and more humid conditions.
- **Fully cured** Seven (7) days.
All figures are quoted at 20°C and 65% relative humidity. Drying will take longer at lower temperatures or higher relative humidity.
- **Coverage per coat** 8-16m²/L (depending on porosity and texture of substrate).
- **WFT per coat** 80μ
- **DFT per coat** 40μ
- **Thinning** Clean Water
- **Clean Up** Thoroughly clean all equipment with water, away from drains.
- **VOC** 21g/L as per EC-07-09. VOC (Volatile Organic Compounds).

RECOMMENDED SUBSTRATE CONDITIONS AND TEMPERATURE

- Ensure all surfaces are clean and dry.
- Remove grease, dust and dirt by washing down with detergent and warm water.
- If mould is present treat with a proprietary mould killer and rinse off.
- All loose, peeling and flaking material or rust must be removed with a scraper or wire brush. Sand the surface smooth and remove all dust.

New Work:

Timber:

Grey weathered timber must be sanded back to the original timber colour. Sand new timber lightly. Prime bare surfaces without delay, certainly within 5 days of preparation with Taubmans Tradex Acrylic Primer Undercoat. Tannin rich timbers such as Cedar should be primed with Taubmans Tradex Oil Based Wood Primer.

Galvanised Iron:

Degrease the surface with Wattyl Roof Wash, allow to dry and prime with Taubmans All Weather Roof Galvanised Iron Primer. Where roofs are used for the collection of drinking water it is recommended that down pipes be disconnected prior to painting and reconnected after the first significant (10 – 15mm) rainfall when painting is complete.

Iron and Steel:

Remove rust with a wire brush, or emery paper. Within 2 hours prime with Wattyl Killrust Metal Primer.

Cement Render and Concrete:

Allow concrete to cure 28 days and apply Taubmans Tradex Exterior Semi Gloss directly to the clean surface.

Fibre Cement:

Ensure surface is clean and dry. Apply Taubmans Tradex Exterior Semi Gloss directly to the clean surface.

Previously Painted Surfaces:

Ensure surface is sound, after preparation to remove dirt etc. Apply Taubmans Tradex Exterior Semi Gloss directly to the clean surface.

Additional Notes:

- Do not apply when the temperature is below 10°C, the humidity is greater than 85%, or if dew or rainfall is likely within 4 hours of application.
- For areas collecting tank water, disconnect tanks before preparation starts. Reconnect after the first significant (10-15mm) rainfall when painting is complete.

INSTRUCTIONS FOR USE

- Stir paint thoroughly with a flat stirrer until contents are uniform and thoroughly mixed.
- Thin with up to 5% water if required.
- Apply 2-3 coats with a quality brush, roller or spray gun. Under normal conditions this paint is touch dry in 30 minutes and may be recoated after 2 hours.

SAFETY DATA

- **Caution** Provide adequate ventilation during use.
- **Spills and Disposal** Do not allow spilt material to enter drains or other watercourses. Absorb spills with sand or other inert material. Do not pour leftover paint down the drain. Unwanted paint should be kept in a sealed container, such as an empty paint can, and disposed of via special waste collection services. Check with your local Council regarding the disposal of empty paint containers. Empty paint containers should be left open in a well ventilated area to dry out. When dry, recycle steel containers via steel can recycling programs. Disposal of empty paint containers via domestic recycling programs may vary between local authorities.
- **M.S.D.S.** A Material Safety Data Sheet (M.S.D.S.) is available on request.
- **First Aid:**
If swallowed **do not** induce vomiting. Give plenty of water to drink. Contact a doctor or the Poisons Information Centre. Phone 0800 764766 (New Zealand).
If in eyes, hold eyes open and flood with water for at least 15 minutes. Contact a doctor if any irritation occurs.
If on skin remove contaminated clothing, wash skin thoroughly with soap and water or a proprietary skin cleanser.
Do not use solvents.

1. This information is provided with respect to the listed Wattyl products. Wattyl recommends that:

(a) The user should check the date of printing, and if more than 24 months have elapsed, should verify with our nearest sales office that the information is still current. (b) you review the Technical Data Sheets (TDS) and Material Safety Data Sheets (MSDS) before you use or handle the product; (c) the product be used only in accordance with the information provided by Wattyl; (d) the product be transported, stored and handled in accordance with the information on the MSDS and relevant TDS; and (e) you thoroughly test the product, using the recommended application method on a sample of intended substrate, before using the product.

2. The information in this technical data sheet was prepared using information gathered during product development. While Wattyl endeavours to update this information and maintain the accuracy and currency of its contents, Wattyl cannot guarantee that the information provided is wholly comprehensive.

3. Wattyl recommends that you conduct such additional investigations as may be necessary to satisfy yourself of the accuracy, currency and comprehensiveness of the information on which you rely in using and handling the product. If you require further information please contact your nearest Wattyl Office.

4. Because we cannot control the way these products may be used, or the conditions they may be exposed to, we can give no express guarantees in respect of these products or their performance. However certain guarantees may be implied by law.


Wattyl (N.Z.) Limited, P. O. Box 1545, Auckland, 1.

Phone 09 820 6700

Fax 09 820 6572

WATTYL (NZ) LTD

INFORMATION HELP LINE: 0800 735551 (New Zealand)



Taubmans Tradex 100% Acrylic Semi Gloss

Data Sheet TA077
Page 3 of 3

If affected by inhalation remove person to fresh air. If breathing difficulties persist or occur later, contact a doctor.

ADDITIONAL DATA

- Available in 10L containers.
- All sanding dusts can be harmful. When sanding any surface wear an appropriate dust mask. Avoid breathing the dust.
- Galvanised iron roofs in severe coastal or industrial environments benefit from priming with Watty! Killrust Galvanised Iron Primer.
- For product advice and assistance telephone toll free 0800 735 551.

1. This information is provided with respect to the listed Watty! products. Watty! recommends that:

(a) The user should check the date of printing, and if more than 24 months have elapsed, should verify with our nearest sales office that the information is still current. (b) you review the Technical Data Sheets (TDS) and Material Safety Data Sheets (MSDS) before you use or handle the product; (c) the product be used only in accordance with the information provided by Watty!; (d) the product be transported, stored and handled in accordance with the information on the MSDS and relevant TDS; and (e) you thoroughly test the product, using the recommended application method on a sample of intended substrate, before using the product.

2. The information in this technical data sheet was prepared using information gathered during product development. While Watty! endeavours to update this information and maintain the accuracy and currency of its contents, Watty! cannot guarantee that the information provided is wholly comprehensive.

3. Watty! recommends that you conduct such additional investigations as may be necessary to satisfy yourself of the accuracy, currency and comprehensiveness of the information on which you rely in using and handling the product. If you require further information please contact your nearest Watty! Office.

4. Because we cannot control the way these products may be used, or the conditions they may be exposed to, we can give no express guarantees in respect of these products or their performance. However certain guarantees may be implied by law.

Watty! (N.Z.) Limited, P. O. Box 1545, Auckland, 1.

Phone 09 820 6700

Fax 09 820 6572

WATTYL (NZ) LTD

INFORMATION HELP LINE: 0800 735551 (New Zealand)

